

AMENDMENTS TO THE CLAIMS:

1. (currently amended) A non-aqueous electrolyte secondary cell comprising:
a cathode comprising $\text{Li}_x\text{Fe}_y\text{PO}_4$ having a particle diameter not greater than 1 micrometer and wherein $0 < x \leq 2$ and $1 \leq y \leq 2$;

an anode ~~wherein said anode comprises~~ comprising:

a sintered carbon material prepared by sintering a carbon material capable of doping/dedoping lithium; and

a conductive agent comprising $\text{D}_s\text{E}_t\text{Li}_u$, wherein D is tin or silicon, E includes another element, Li is lithium, and $s > 0$, $t > 0$, and $u > 0$; and

a non-aqueous electrolyte solution.

2. (canceled)

3. (canceled)

4. (currently amended) A non-aqueous electrolyte secondary cell comprising:

a cathode having a molded body comprising a cathode active material and a conductive agent, said active material comprising $\text{Li}_x\text{Fe}_y\text{PO}_4$ and having a particle diameter not greater than 1 micrometers wherein $0 < x \leq 2$ and $1 \leq y \leq 2$;

an anode having a molded body comprising a material selected from the group consisting of an anode active material capable of doping/dedoping lithium[[,]] and
a conductive agent comprising $\text{D}_s\text{E}_t\text{Li}_u$, wherein D is tin or silicon, E includes another element, Li is lithium, and $s > 0$, $t > 0$, and $u > 0$, and mixtures thereof; and

a non-aqueous electrolyte solution.

5-13. (canceled)

14. (previously presented) The non-aqueous electrolyte secondary cell of Claim 1, wherein said carbon material is selected from the group consisting of non-graphitizable carbon, graphitizable carbon, graphite, and mixtures thereof.

15. (previously presented) The non-aqueous electrolyte secondary cell of Claim 1, wherein said non-aqueous electrolyte solution comprises an electrolyte salt and a non-aqueous solvent.

16. (previously presented) The non-aqueous electrolyte secondary cell of Claim 15, wherein said electrolyte salt is a lithium salt having ion conductivity.

17. (previously presented) The non-aqueous electrolyte secondary cell of Claim 16, wherein said lithium salt is selected from the group consisting of LiClO_4 , LiAsF_6 , LiPF_6 , LiBF_4 , $\text{LiB}(\text{C}_6\text{H}_5)_4$, LiCl , LiBr , $\text{CH}_3\text{SO}_3\text{Li}$, $\text{N}(\text{C}_n\text{F}_{2n}\text{SO}_2)_2\text{Li}$, and mixtures thereof.

18. (previously presented) The non-aqueous electrolyte secondary cell of Claim 15, wherein said non-aqueous solvent is selected from the group consisting of propylene carbonate, ethylene carbonate, 1,2-dimethoxyethane, 1,2-diethoxyethane, diethyl carbonate, methyl ethyl carbonate, dimethyl carbonate, γ -butyrolactone, tetrahydrofuran, 1,3-dioxolane, 4-methyl-1,3-dioxolane, diethyl ether, sulfolane, methyl sulfolane, acetonitrile, propionitrile, and mixtures thereof.

19. (previously presented) The non-aqueous electrolyte secondary cell of Claim 4, wherein said anode active material comprises a carbon material selected from the group consisting of non-graphitizable carbon, graphitizable carbon, graphite, and mixtures thereof.

20. (canceled)

21. (canceled)

22. (currently amended) The non-aqueous electrolyte secondary cell of Claim 4, wherein ~~said anode conductive agent~~ D_sE_t includes a material is selected from ~~the a~~ group of materials consisting of SiB_4 , SiB_6 , Mg_2Si , ~~$NiSi_2$~~ , $TiSi_2$, $MoSi_2$, $CoSi_2$, $NiSi_2$, $CaSi_2$, $CrSi_2$, Cu_5Si , $FeSi_2$, $MnSi_2$, $NbSi_2$, $TaSi_2$, VS_i , WSi_2 , $ZnSi_2$ and mixtures thereof.

23. (previously presented) The non-aqueous electrolyte secondary cell of Claim 4, wherein said non-aqueous electrolyte solution comprises an electrolyte salt and a non-aqueous solvent.

24. (previously presented) The non-aqueous electrolyte secondary cell of Claim 23, wherein said electrolyte salt is a lithium salt having ion conductivity.

25. (previously presented) The non-aqueous electrolyte secondary cell of Claim 24, wherein said lithium salt is selected from the group consisting of $LiClO_4$, $LiAsF_6$, $LiPF_6$, $LiBF_4$, $LiB(C_6H_5)_4$, $LiCl$, $LiBr$, CH_3SO_3Li , $N(C_nF_{2n}SO_2)_2Li$, and mixtures thereof.

26. (previously presented) The non-aqueous electrolyte secondary cell of Claim 23, wherein said non-aqueous solvent is selected from the group consisting of propylene carbonate, ethylene carbonate, 1,2-dimethoxyethane, 1,2-diethoxyethane, diethyl carbonate, methyl ethyl carbonate, dimethyl carbonate, γ -butyrolactone, tetrahydrofuran, 1,3-dioxolane, 4-methyl-1,3-dioxolane, diethyl ether, sulfolane, methyl sulfolane, acetonitrile, propionitrile, and mixtures thereof.

27. (new) The non-aqueous electrolyte secondary cell of Claim 1, wherein the cathode further comprises a conductive material and a binder.

28. (new) The non-aqueous electrolyte secondary cell of Claim 1, wherein the anode further includes a molded and sintered current collector material combined with said sintered carbon material.

29. (new) The non-aqueous electrolyte secondary cell of Claim 1, wherein E is selected from a list of elements and compounds consisting of B₄, B₆, Mg₂, Ti, Mo, Co, Ni, Ca, Cr, Cu₅, Fe, Mn, Nb, Ta, V, W, Mg₂SaANi_z.

30. (new) The non-aqueous electrolyte secondary cell of Claim 4, wherein said cathode further comprises a conductive material and a binder.

31. (new) The non-aqueous electrolyte secondary cell of Claim 4, wherein the anode further includes a molded and sintered current collector material combined with said sintered carbon material.

32. (new) The non-aqueous electrolyte secondary cell of Claim 4, wherein E includes Mg₂SaANi_z.